

**PRODUCTION OF 3A-ZEOLITE MOLDED BODY**

Patent Number: JP5147926  
Publication date: 1993-06-15  
Inventor(s): KAWAMOTO TAIZO; others: 04  
Applicant(s): TOSOH CORP  
Requested Patent: ☐ JP5147926  
Application Number: JP19910337978 19911128  
Priority Number(s):  
IPC Classification: C01B33/34; B01D53/28; B01J20/18  
EC Classification:  
Equivalents:

---

**Abstract**

---

PURPOSE:To obtain a 3A-zeolite molded body having excellent spalling resistance and high water adsorption.  
CONSTITUTION:A molded body consisting of synthetic 4A-zeolite and attapulgite type clay in (80:20) to (70:30) weight ratio is subjected to ion exchange treatment by which  $\geq 80\%$  of cations in the 4A-zeolite are exchanged for potassium ions, thus the objective 3A-zeolite molded body is produced.

---

Data supplied from the esp@cenet database - I2